



## Conduit Data

British Standard (BS4568-1970)

Nominal Dimension (mm)	Outside Diameter (mm)		Wall Thickness (mm)	Length of Thread (mm)		Weight (Kg/M)		Length (M)
	Minimum	Maximum		Minimum	Maximum	Minimum	Maximum	
16	15.7	16	1.4	11.5	13.5	0.452	0.531	3.75
20	19.7	20	1.6	13.0	15.0	0.643	0.783	3.75
25	24.6	25	1.6	16.0	18.0	0.811	0.995	3.75
32	31.6	32	1.6	18.0	20.0	1.069	1.301	3.75

It is manufactured from hot-dipped galvanised plate rolling. Featured by uniformity Zinc coat, good surface finish, smooth surface both inside and outside the conduit wall, free from black spots and bubbles, strong corrosion resistance and long life, Height of inner welding line is less than 0.3mm, it is applied in all severe environments and provides good protection for the electrical raceway system. Conduit is Hot dipped Galvanised, Class 4 and has a zinc coating usually 250g-300g per square meter which has a strong corrosion resistance.

### Head Office

5 Mathieson Road  
Rutherglen, Glasgow,  
G73 1DA.

**T** 141 647 3111

**F** 0141 613 1338

**E** sales@aitkenscotland.co.uk

### Leeds Branch

Unit 2A Silver Royd Hill,  
Silver Royd Business Park,  
Silver Royd Hill, LS12 4QQ.

**T** 0113 255 1111

**F** 0113 255 1101

**E** leeds@aitkenscablemanagement.co.uk

### Manchester Branch

Unit N9 Central Park Trading Estate,  
Mosley Road, Trafford Park,  
M17 1PG.

**T** 0161 872 6214

**F** 0161 872 7411

**E** manchester@aitkenscablemanagement.co.uk